

# Marini Blue Marble



## Finishes

Width

Polished Honed Sand Blasted Sand Blasted & Brushed Bush Hammered

\*Specialised finishes available.

Available Sizes (mm)

Length


	100	200	300	400	500	600	700	800	900	1000	1100	1200
100												
200												
300												
400												
500												
600												
700												
800												
900												
1000												

Available

Not Available



## Sealing Requirement



#### Stone Properties

Property	Abrasion Strength (cm3/50cm2)	Bulk Density (kg/m3)	Compressive Strength (Mpa)	Flexural Strength Under Load (Mpa)	Open Porosity (%)	Salt Resistance	Slip Resistance (SRV)
Test Method	EN 14157	EN 1936	EN 1926	EN 12372	EN 1936	AS/NZS 4456.10	AS 4586
Result		2710	130	15.6		AA	P1-P5

- General technical data; please contact us for specific projects. We offer materials with characteristics which can be changed to suit your requirements.
- The technical data and in general the information contained in this technical sheet is based on tests considered to be reliable. We do not guarantee their accuracy when compared to subsequent tests due to the inherent variability of natural stone. If test results are critical please request reports for each critical factor.



#### Cleaning & Maintenance

Natural stone is considered a high quality covering, which fulfils all the physical, chemical, and building requirements to carry out a good project with proven success, thanks to its durability and the low maintenance cost in comparison to other materials like artificial stone.



The hardness and lifespan of natural stone can be increased with an appropriate choice of finish, treatment and further maintenance.



Water is the best cleaning solution. However, when it comes to cleaning and disinfecting, it is advisable to use pH balanced cleaners (7-10 pH).



Never use aggressive detergents such as bleach, ammonia, descalers, etc.



Never use metal utensils (such as steel wool) as they may scratch the surface

Lithic Australia

39 Canavan Drive **Beresfield NSW** 2322 Australia Phone: (02) 4966 8474 info@lithicaustralia.com.au 133 Victoria Road Rozelle NSW 2039 Australia Phone: (02) 9030 8454 info@lithicaustralia.com.au

www.lithicaustralia.com.au
















If the stain persists, click **HERE** or scan the QR code to read an arcticle on how to clean natural stone depending on the type of stain.

#### The article includes solutions for:

- General Maintenance
- Cement & Grout Residue

- Rust
- Efflorescence
- Organic Stains
- Soap Scum

- Grease/Fat/Oil
- Epoxy, Wax, Glue
- Dirty Grout

#### **How To Clean Natural Stone**



