

Gossamer Light Marble


Finishes



Type And Size (mm)

Finish	Paver	Tile	Slab	Cobblestone	Wall Cladding	Custom
Honed			20x3100x1800			

Sealing Requirement



Stone Properties

Property	Abrasion Strength (cm3/50cm2)	Bulk Density (kg/m3)	Compressive Strength (Mpa)	Flexural Strength Under Load (Mpa)	Open Porosity (%)	Salt Resistance	Slip Resistance (SRV)
Test Method	EN 14157	EN 1936	EN 1926	EN 12372	EN 1936	AS/NZS 4456.10	AS 4586
Result	13.6	2709	105.52	14.65	0.139		PΊ

- General technical data; please contact us for specific projects. We offer materials with characteristics which can be changed to suit your requirements.
- The technical data and in general the information contained in this technical sheet is based on tests considered to be reliable. We do not guarantee their accuracy when compared to subsequent tests due to the inherent variability of natural stone. If test results are critical please request reports for each critical factor.